

ANNEX II SAMPLE INFORMATION

				SPI WATER VISCOSITY 1.5%; 75C				
RR#2 Sample ID	Carrageenan Type	Producer	Approx. Gum Content (%)	SIAP 5/04 (cps)	SIAP 7/05 (cps)	FMC 6/04 (cps)	FMC 7/05 (cps)	AVERAGE (cps)
9939-03	Kappa IPA	FMC	75%	28	24	36	34	31
7834-03	Radula IPA	FMC	82%	690	650	745	728	703
MW-kappa	Kappa GP	CPK	79%	48	44	60	64	54
MW-iota	Iota IPA	CPK	79%	36	35	42	44	39
TS-C6336	Radula GP	Danisco	77%	32	28	35	37	33
13754(Rad)	Radula IPA	Degussa	78%	44	42	53	49	47
13754(Chon)	Chondrus IPA	Degussa	62%	26	23	33	30	28
20ND	PES Kappa	Shemberg	67%	24	20	26	27	24
70C1	PES Kappa	Shemberg	66%	28	23	26	28	26
01T1	PES Iota	Shemberg	66%	19	15	15	20	17
6371-03	Kappa IPA	FMC	85%	NA	7	8	8	8
RR#1 Sample ID								
2217-01	Kappa IPA	FMC	84%			12	12	12
6370-03	Kappa IPA	FMC	85%			9	9	9